

Chemdeck TF

3- Component, thixotropic, non-broadcast, antiskid PU flooring system for deck coating and antiskid coatings.

Product Description

Chemdeck TF is a 3-component, high-build PU floor coating system formulated as a textured top coat for an antiskid system. It offers a unique advantage of a high-strength, aesthetically pleasing anti-skid system without the use of abrasive coarse silica sand.

Salient Features:

- Good chemical and mechanical resistance
- Easy application
- Excellent adhesion to substrate
- Glossy finish
- Seamless slip-resistant surface
- Easy to clean and maintain
- Wide range of colour options
- Slip resistance without quartz broadcast
- Variety of antiskid textures possible

Uses

- Slip-resistant coating for concrete and cement screed
- For multi-storeyed and underground car park
- For maintenance hangars and for wet process areas, e.g., the beverage and food industry
- For storage and assembly halls, maintenance workshops, garages, and loading ramps.

Product Data

Appearance / colour:	Chemdeck TF[R] Resin: Chemdeck TF [H] Hardener: Pigment :	White viscous liquid Brown liquid Coloure paste <small>(supplied separately not part of kit)</small>
Storage conditions /shelf life	12 months from date of mfg. If stored properly in undamaged seal packaging, at a temperature between 5 °C - 30 °C. It should be kept in a cool, well-ventilated area, away from heat, direct sunlight, sparks, and children.	

Chemical Resistance

Excellent resistance is observed against distilled water, detergent solutions, alkalis, and acids.

Mechanical /Physical properties

Physical properties

Property	Test Method	Value and Unit
Finish	CPI* 1001	Anti-skid, Glossy/matt
Pot Life @ 30 °C	CPI 1002	20 minutes
Surface Dry	CPI 1002	2 hours
Skid Resistance (ASTM E303)	(ASTM E303)	48
Elongation at break	ASTM D 638	30-40%
Pull off Adhesion test	ASTM D 4541	Concrete Failure @ 18 Kg/cm ²
Abrasion Resistance[Taber]	ADTM D 4060	50 mg loss
Compressive strength	ASTM D 695	>500 kg/cm ²
Flexural Strength	ASTM C580	>150 kg/cm ²
Tensile strength	ASTM D638	>200 kg/cm ²
Shore Hardness	ASTM D2240	Shore D 75-85
Shelf Life	-	12 months in original unopened Container when stored between 5- 40 °C

Method of Application

All Chemsol Products are recommended to be applied only by Approved Applicators and should be used after using proper PPE's like Gloves, mask, goggles, etc.

Substrate Quality

The CDS (clean, dry, sound) test must be conducted before the application of primer to the concrete substrate. The substrate must be free of all contaminants such as dirt, oil, grease, coatings, and surface treatments, etc. If in doubt, apply a test area first.

Application conditions



Substrate temperature: 10-40 °C



Substrate moisture content: - <5%



Relative humidity: 80%max

Note: The substrate temperature must be at least 30C above the prevalent dew point temperature to reduce chances of condensation on the floor.

Priming

The concrete surface, after proper and thorough surface preparation, has to be primed with an appropriate primer like Chembase 150/160. After priming, allow the surface to cure for 4-5 hours. Depending on the condition of the surface, an additional layer of Epoxy screed/ Epoxy Putty with chembase 150/160 and graded sand may be required to level out the surface undulations before application of the Topcoat of chemdeck TF.

Application of Chemdeck TF coat

Ensure that the underlying coat is thoroughly cured and is dust-free. Add pigment paste to the resin part and Stir mechanically for 1 minute in order to disperse the pigments into the resin uniformly. Now add hardener and continue stirring for a further 2 minutes with a motorized helical paint stirrer until a uniform mix has been obtained. Once mixed material should be used within its specified pot life; the material is to be applied in a single coat application onto the primed surface/ epoxy screed. Spread material evenly using a notch trowel (0.5 mm Notch) and roll it evenly with a special "chemsol textured roller" within 10- 15 min. to obtain the desired finish.

Curing Schedule

Vehicular movement on Chemdeck TF should be allowed ideally after 3 days of application, depending upon the ambient temperature & humidity. This is a fast-curing system. Refer to the following table to know how quickly the floor can be brought to service

Temp.(deg C)	Foot traffic	Full cure
10°C	24 hours	120 hours
20°C	12 hours	72 hours
30°C	8 hours	72 hours

Cleaning of Tools

Clean all tools and application equipment with thinner PT 36 immediately after use. Hardened and/or cured material can only be removed mechanically.

Coverage

Pre weighed kit to cover 13-16 sqm/kit 0at 500 micron thickness

Handling & Safety

Keep the containers tightly sealed when not in use. Avoid skin contact and inhalation of fumes (if any). While spraying, it is advised to wear a mask. If it comes in contact with the body, wash affected parts with plenty of soap and water. In case of persistent irritation, contact a physician.

Disclaimer: The Information provided is based on our experience, thorough investigations & sophisticated testing methods, but due to the vast number of applications and usage methods, Chemsol Polymer Industries cannot accept responsibility of any kind for any particular result. It is the responsibility of the user to verify the suitability of the product for their end use, and in accordance with the rules and regulations of that country /territory. All information provided pertaining to our products should be treated only as a guidance tool without any guarantee or warranty of any sort.

* All CPI test methods are our scientifically designed internal test methods which can be shared upon

Factory Address:

Plot No. C93, MIDC, Additional
Jejuri, Tal: Purandar, District, Pune,
Maharashtra, India. PIN: 412303

Correspondence Address:

Office No. 101, G wing, KK
Market, Dhankawadi, Pune-
411043.

Enquiry:

Mobile: +91-7720002824 | 020-24371247
For Sales: sales@chemsolpoly.com
For Materials: purchase@chemsolpoly.com