

Product Description

Floorchem primer is a 2-component, PU-based floor coating system formulated as a Primer coat for Pu flooring system.

Uses

Specially recommended as a base coat or binding agent for antiskid systems built by silica sand broadcasting.

Salient features

- Good chemical resistance
- Easy application, durable
- Excellent adhesion to substrate
- Good flow
- · Long Pot Life



Product Data

Appearance / colour:	Floorchem primer [R] Resin: Floorchem primer [H] Hardener: Floorchem primer Aggregates:	pale yellow liquid Brown liquid White powder
Storage conditions /shelf life	12 months from date of mfg. If stored properly in undamaged seal packaging, at a temperature between 50 °C- 300 °C it should be kept in a cool, well-ventilated area, away from heat, direct sunlight, sparks, and children.	

Mechanical /Physical properties

Property	Test Method	Value and Unit
Mixing Ratio	NA	Pre weighed kit
Solid content	CPI* 1001	approx 100%
Pot Life @ 30 °C	CPI 1002	20 minutes
Surface Dry	CPI 1002	3 hours
Hard Dry [Open for foot traffic]	CPI 1002	24 Hours
Full Cure [Vehicular Movement]	CPI 1002	72 Hours
Mechanical properties		
Elongation at break	ASTM D 638	52-55%
Pull off Adhesion test	ASTM D 4541	Concrete Failure @ 18 Kg/cm2
Tensile strength	ASTM D 638	11 MPa
Abrasion Resistance[Taber]	ADTM D 4060	35-40 mg loss/1000 cycles
Shelf Life	-	12 months in original unopened Container when stored between 5 °C - 40 °C

Method of Application

All Chemsol Products are recommended to be applied only by Approved Applicators and should be used after using proper PPEs like Gloves, masks, goggles, etc.

Substrate Quality

The CDS (clean, dry, sound) test must be conducted before the application of primer to the concrete substrate. The substrate must be free of all contaminants such as dirt, oil, grease, coatings, and surface treatments, etc. If in doubt, apply a test area first.



Application Conditions:



Substrate temperature: 10-40 °C



Substrate moisture content: - <5%



Relative humidity: 80%max

Application of floorchem Primer

Stir the resin part mechanically for 1 minute, then add the hardener and again stir it with a motorised helical paint stirrer until a uniform mix has been obtained. Pour the material on the floor and spread it with a notch trowel.

Curing Schedule

Refer to the following table to know how quickly the floor can be brought to service

Foot traffic	Full cure
48 hours	120 hours
36 hours	72 hours
24 hours	72 hours
	48 hours 36 hours

Cleaning of Tools

Clean all tools and application equipment with thinner PT 36 immediately after use. Hardened and/or cured material can only be removed mechanically.

Packing

Floorchem primer is available in pre preweighed kit of 30 liters.

Handling & Safety

Keep the containers tightly sealed when not in use. Avoid skin contact and inhalation of fumes (if any). While spraying, it is advised to wear a mask. If it comes in contact with the body, wash affected parts with plenty of soap and water. In case of persistent irritation, contact a physician.

Disclaimer: The Information provided is based on our experience, thorough investigations & sophisticated testing methods, but due to the vast number of applications and usage methods, Chemsol Polymer Industries cannot accept responsibility of any kind for any particular result. It is the responsibility of the user to verify the suitability of the product for their end use and in accordance with the rules and regulations of that country /territory. All information provided pertaining to our products should be treated only as a guidance tool without any guarantee or warranty of any sort.

^{*}Note: The substrate temperature must be at least 30 °C above the prevalent dew point temperature to reduce chances of condensation on the floor.

^{*} All CPI test methods are our scientifically designed internal test methods which can be shared upon request.